

# TROPICADHESIVE® CONTACT ADHESIVE (43 - 3015)

Date: Nov 2016 Version: R 2

Printing date: Nov 2016

# ĒĒT

DATA

CHNICAL

# PRODUCT DESCRIPTION

SAAF Tropic Brand 43-3015 is a one component, multi-purpose contact adhesive based on Polychloroprene which use to bond plastic laminate, aluminum, steel, wallboard, wood, masonry, Formica, rubber and canvas.

# **FEATURES AND BENEFITS**

- · Applied easily by Roll or brush
- Specially developed for hot climate
- Use on porous & non-porous substrates.
- Has a long open time and good wet tack
- Fast drying
- Excellent bonding & adhesion strength
- Excellent resistance to heat, humidity & detergents
- 60 minutes bonding range

# **APPLICATION TOOLS**

Brush, Roller or any suitable applicator.

# **STANDARDS COMPLIANCE**

**DIN 16860** 

# **RECOMMENDED USES**

- For installing of indoor/outdoor carpeting due to its excellent moisture resistance.
- For bonding leather, rubber, shoe material, wood & Formica
- Bonding of decorative laminates made of Wood, Steel, and Plastics etc
- To adhere tapered Polyurethane insulation to each other & with roof substrate
- To adhere filler board protection to water proofing membrane
- Bonding synthetic rubber floor tiles (Stud tiles)
- Bonding wide range of PVC wall skirting & PVC profiles

# **STORAGE**

- Should be stored tightly closed and away from direct sunlight in a cool, well-ventilated area between 5°C to 39°C
- · Protect from freezing
- Close container tightly when not in use
- Store away from ignition sources

# **SURFACE PREPARATION**

All surfaces must be clean, dry and free from dust, dirt, paint, loose materials, oil, grease, sealers, curing compounds, waxes and all other contaminations.

# **PACKAGING**

750 ml Can, 3.8 Lit. Gallon, 20 Lit. Pail & 200 Lit. Drum.

TECHNICAL DATA				
BASEMATERIAL	Synthetic Resin + Polychloroprene		OPEN TIME	3 - 5 Minutes
COLOR	Pale Yellow		SETTING TIME	30 Minutes
VISCOSITY AT 25°C ASTM D2196	3000 – 4000 CPS (Sp. # 4 @ 20 rpm)		PRESSING TIME	Approx.10 - 60 Min.
SPECIFIC GRAVITY GM/CM3 ASTM D1475	0.84 - 0.89		FLASH POINT ASTM D3278	-17°C.
SOLID CONTENTS ASTM D1644	25 - 28%		VOC ASTM D2369	410 g/l
COVERAGE (APPROX.)	4 – 6 Kg/ m <sup>2</sup>		SERVICE TEMP	-5°C to 80°C
ADHESION STRENGTH AFTER AGING % CHANGE	Stable with no Change		STORAGE STA- BILITY	Stable (No change at 55°C)
RESISTANCE OF THE DRY ADHESIVE	Can Resist to: Heat up to 90°C, Moistures, Detergents, Non- Aromatic fuels & Oils.		FLAMMABILITY	Inflammable while it is wet
DRYING TIME	60 Minutes (Depends on absorption & Temp.)		DILUTION	Do not dilute

F/QC/13: R2

The information provided here is based on our test results and to the best of our current knowledge. The recommendations and suggestions here in are made to facilitate the application of the product without any guarantee or representation to results. We recommend you to ensure that the product meets all your requirements prior to the application.



# TROPICADHESIVE® **CONTACT ADHESIVE (43 - 3015)**

Date: Nov 2016 Version: R2

Printing date: Nov 2016

# CHNICAL DATA SHEE

# **APPLICATION METHOD**

- · Stir thoroughly before using.
- Apply adhesive generously in a uniform thickness on both surfaces in a smooth pattern and cover each surface with minimum of 80% and cover the edges with 100%.
- Porous surfaces may require 2 coats of adhesive.
- Allow both surfaces to dry until the adhesive is no longer tacky (3 5 minutes).
- Position surfaces carefully before assembly.
- No adjustment is possible after contact.
- Spacers such as dowels or strips of laminate may be used to prevent premature adhesive/adhesive contact and bonding.
- Slide out the spacers and apply uniform pressure, working toward the edges.
- A 3 inch roller with maximum body pressure should be used to help ensure adequate contact and bonding, especially on the edges.
- Bonded assemblies can be machined, trimmed or finished immediately after bonding.

# **LIMITATIONS**

Do not dilute the product with any type of solvents

### **CLEANING & DISPOSAL**

- Excess adhesive may be removed immediately after the application
- The Tools & the excess material should be cleaned immediately by SAAF CPVC & PVC Cleaner or any common solvents like xylene, white spirit, etc. before it gets dry
- Dispose the waste according to the local regulations

# SHELF LIFE

12 months shelf life when stored in it's original unopened container between 5°C to 39°C.

# **HEALTH & SAFETY**

The product is inflammable, keep it away from heat, sparks, open flame & other ignition sources, vapors may ignite explosively. Use only in well ventilated areas.

The product should not be swallowed or allowed to come into contact with skin and eyes. Use of suitable protective gloves and goggles is advisable.

If eyes are affected with the adhesive rinse with excess amount of clean fresh water and seek for medical advice. If swallowed seek medical attention immediately and do not induce vomiting help.

# **HMIS Rating**

**HEALTH** 2 **FLAMMABILITY** 3 REACTIVITY

N = No information provided 0 = Minimal;1 = Slight;2 = Moderate: 3 = Serious: 4 = Severe:

# **ADDITIONAL INFORMATION**

# SAAF IS ALSO MANUFACTURES THE FOLLOWING RANGE OF PRODUCTS

- Solvent Based Adhesives
- Water Based Adhesives
- · Flooring Adhesives
- Putties & Sealants
- Coatings
- Concrete Admixtures

For further information, kindly visit our website www.tigind.com

F/QC/13: R2

The information provided here is based on our test results and to the best of our current knowledge. The recommendations and suggestions here in are made to facilitate the application of the product without any guarantee or representation to results. We recommend you to ensure that the product meets all your requirements prior to the application.